AMENDMENTS TO THE CLAIMS:

1. (Original) A storage medium, comprising:

a metallic underlayer;

a ferroelectric data layer over said metallic underlayer; and

a layer over said ferroelectric data layer having a charge migration rate faster than a

charge migration rate of said ferroelectric data layer.

2. (Original) The storage medium of claim 1, wherein said layer over said ferroelectric data

layer comprises a conducting layer.

3. (Original) The storage medium of claim 1, wherein said layer over said ferroelectric data

layer directly contacts a top surface of said ferroelectric data layer.

4. (Currently amended) The storage medium of claim 2, wherein said conducting layer

comprises at least one one of:

silicon; and

a doped perovskite.

5. (Original) The storage medium of claim 1, wherein said charge migration time is less than

approximately 10⁻¹⁰ second.

6. (Original) The storage medium of claim 2, wherein a thickness of said conducting layer is

within a range of approximately 5 Å to approximately 25 Å.

2

Serial No. 10/697,271

Docket No. YOR920030500US1 (YOR.495)

7. (Original) The storage medium of claim 1, wherein said metallic underlayer comprises SrRuO₃.

8. (Original) The storage medium of claim 1, wherein said ferroelectric data layer comprises at least one of:

```
PZT (Pb(Zr<sub>x</sub> Ti<sub>1-x</sub>)O<sub>3</sub>);

SBT (SrBi<sub>2</sub>Ta<sub>2</sub>O<sub>9</sub>);

BaMgF<sub>4</sub>;

STN (Sr<sub>2</sub>(Ta<sub>1-x</sub> Nb<sub>x</sub>)<sub>2</sub>O<sub>7</sub>); and

NFM (COVA).
```

- 9. (Original) The storage medium of claim 5, wherein a thickness of said conducting layer is approximately 15 Å.
- 10. (Withdrawn) A memory apparatus, comprising

a support mechanism to support and move a ferroelectric storage medium, said ferroelectric storage medium comprising a metallic underlayer, a ferroelectric data layer over said metallic underlayer, and a conducting layer over said ferroelectric layer having a charge migration rate faster than a charge migration rate of said ferroelectric data layer.

- 11. (Withdrawn) The memory apparatus of claim 10, further comprising: a read/write head for accessing said ferroelectric storage medium.
- 12. (Withdrawn) The memory apparatus of claim 11, wherein said read/write head includes an electrometric sensor for reading information from said ferroelectric storage medium.

Serial No. 10/697,271

Docket No. YOR920030500US1 (YOR.495)

13. (Withdrawn) The memory apparatus of claim 12, wherein said electrometric sensor

comprises:

an open-gate finFET.

14. (Withdrawn) The memory apparatus of claim 12, wherein said electrometric sensor

comprises a plurality of electrometric sensing elements,

said plurality of electrometric sensing elements arranged linearly in at least one

dimension.

15. (Withdrawn) The memory apparatus of claim 14, wherein said plurality of electrometric

sensing elements are arranged in an x-axis dimension and in a y-axis dimension.

16. (Original) A method of manufacturing a storage medium, said method comprising:

applying a layer of ferroelectric material over a metallic underlayer; and

applying a layer of conducting material over said ferroelectric layer.

17. (Original) The method of claim 16, wherein said conducting layer comprises at least one

of:

silicon; and

a doped perovskite.

18. (Original) The method of claim 16, wherein a thickness of said conducting layer is

within a range of approximately 5 Å to approximately 25 Å.

4

Serial No. 10/697,271

Docket No. YOR920030500US1 (YOR.495)

19. (Original) The method of claim 18, wherein a thickness of said conducting layer is approximately 15 $\rm \mathring{A}$.

20. (Original) The method of claim 16, wherein said metallic underlayer comprises SrRuO₃.